

**MULTISPEC®**  
**MCT**  
**MULTIPURPOSE  
CLEAR TOPCOAT**



- Waterborne, acrylic polyurethane for superior protection. Dries to a tough, crystal clear finish.
- Durable, long-wearing finish for architectural and product finishing applications.
- Protects against moisture, stains, oils and most household chemicals. Chip, mar and abrasion resistant.
- Recommended for multicolor finishes on areas or surfaces subject to repeated handling or soiling.
- User and environment

**friendly. VOC compliant.**

- **Protects and beautifies all natural interior wood surfaces.**
- **Fast drying, easy to apply. Low odor, non-toxic.**
- **Apply with synthetic brush, foam brush, pad applicator or appropriate stainless steel spray equipment. Water reducible.**

---

## **TECHNICAL SUMMARY**

Coverage: Approximately 400-500 sq. ft./gal. depending on type of applicator, number of coats and surface texture.

Dry Time: ASTM D1640. Tack free 15 mins.

Thorough dry 65 mins.

Scrub Resistance: ASTM D2486. Pass 800 cycles.

Hardness: ASTM D3363. Pass H-2H pencil hardness.

Impact: ASTM D2794. Pass 160 inch pounds direct.

Flexibility: ASTM D1237. Pass 1/8" Mandrell Bend.

Washability: ASTM D3450. Reflectance recovery 99.9%.

Mar Resistance: Excellent.

Adhesion: Crosshatch, pass; intercoat: pass, within 48 hours.

Sward Hardness: ASTM D2134. 38%.

Abrasion Resistance: Taber CS 10 wheel, 500 gms. 70 mgms loss/1000 cycles.

Chemical Resistance: ASTM D1308.

Superior resistance to ethyl alcohol, isopropanol and hot wax.

V.O.C./V.O.S Content: 230 grams/liter; 1.91 lbs. per gallon.

Caution: Sensitive to temperature extremes. Read label warnings and instructions prior to beginning job.

---

## **ORDERING INFORMATION**

Available in quarts (6 per carton) and in gallons (2 per carton). Shipping wt. 2.2 lbs. per quart;  
8.6 lbs. per gallon.

Order #9S146 for High Gloss. Order #9S147 for Low Gloss.

FOR MORE INFORMATION, CALL 800-536-5456, FAX 708-656-5055